ULTRAFIT WINDOW FILM

VIVID COMFORT Series

VLT 5%
TSER 63%
IR REJECTION 71%

VC 05 BK

Permanent Gratification

Chosen as one of the most popular selections of metallic window films in the industry, experience the comfortability and timeless features of the Vivid Comfort window film today.

SPECIFICATIONS	
Visible Light Transmission	5 %
Visible Light Reflection (Int) / (Ext)	5 % / 5 %
UV Rejection	99 %
IR Rejection	71 %
Solar Heat Gain Coefficient	0.45
Shading Coefficient	0.49
Total Solar Energy Rejection	63 %

AUTOMOTIVE FILMS

HAZE ★★★★★
SAFETY ★★
FADE OUT ★★★★★
SHIRINKAGE ★★★★
UV BLOCK ★★★★★
BLOCKS HEAT ★★★★★

ULTRAFIT WINDOW FILM

VIVID COMFORT Series

VLT 17%
TSER 55%
IR REJECTION 55%

VC 15 BK

Permanent Gratification

Chosen as one of the most popular selections of metallic window films in the industry, experience the comfortability and timeless features of the **Vivid Comfort** window film today.

SPECIFICATIONS	
Visible Light Transmission	17 %
Visible Light Reflection (Int) / (Ext)	5 % / 5 %
UV Rejection	99 %
IR Rejection	55 %
Solar Heat Gain Coefficient	0.54
Shading Coefficient	0.59
Total Solar Energy Rejection	53 %

AUTOMOTIVE FILMS

HAZE ★★★★★
SAFETY ★★
FADE OUT ★★★★★
SHIRINKAGE ★★★★
UV BLOCK ★★★★★
BLOCKS HEAT ★★★★★

ULTRAFIT WINDOW FILM

VIVID COMFORT Series

VLT 26%
TSER 50%
IR REJECTION 53%

VC 25 BK

Permanent Gratification

Chosen as one of the most popular selections of metallic window films in the industry, experience the comfortability and timeless features of the **Vivid Comfort** window film today.

SPECIFICATIONS	
Visible Light Transmission	26 %
Visible Light Reflection (Int) / (Ext)	5 % / 6 %
UV Rejection	99 %
IR Rejection	53 %
Solar Heat Gain Coefficient	0.56
Shading Coefficient	0.62
Total Solar Energy Rejection	50 %

AUTOMOTIVE FILMS

HAZE ★★★★★
SAFETY ★★
FADE OUT ★★★★★
SHIRINKAGE ★★★★
UV BLOCK ★★★★★
BLOCKS HEAT ★★★★★

ULTRAFIT WINDOW FILM

VIVID COMFORT Series

VLT 37%
TSER 42%
IR REJECTION 49%

VC 35 BK

Permanent Gratification

Chosen as one of the most popular selections of metallic window films in the industry, experience the comfortability and timeless features of the **Vivid Comfort** window film today.

SPECIFICATIONS	
Visible Light Transmission	37 %
Visible Light Reflection (Int) / (Ext)	7 % / 7 %
UV Rejection	99 %
IR Rejection	49 %
Solar Heat Gain Coefficient	0.62
Shading Coefficient	0.69
Total Solar Energy Rejection	42 %

AUTOMOTIVE FILMS

HAZE ★★★★★
SAFETY ★★
FADE OUT ★★★★★
SHIRINKAGE ★★★★
UV BLOCK ★★★★★
BLOCKS HEAT ★★★★★

ULTRAFIT WINDOW FILM

VIVID COMFORT Series

VLT 46%
TSER 41%
IR REJECTION 51%

VC 50 BK

Permanent Gratification

Chosen as one of the most popular selections of metallic window films in the industry, experience the comfortability and timeless features of the **Vivid Comfort** window film today.

Visible Light Transmission	46 %
Visible Light Reflection (Int) / (Ext)	8 % / 8 %
UV Rejection	99%
IR Rejection	51%
Solar Heat Gain Coefficient	0.62
Shading Coefficient	0.71
Total Solar Energy Rejection	41%

AUTOMOTIVE FILMS

HAZE ★★★★★
SAFETY ★★
FADE OUT ★★★★★
SHIRINKAGE ★★★★
UV BLOCK ★★★★★
BLOCKS HEAT ★★★★★

ULTRAFIT WINDOW FILM

VIVID COMFORT Series

VLT 75%
TSER 23%
IR REJECTION 32%

VC 70

Permanent Gratification

Chosen as one of the most popular selections of metallic window films in the industry, experience the comfortability and timeless features of the **Vivid Comfort** window film today.

SPECIFICATIONS	
Visible Light Transmission	75 %
Visible Light Reflection (Int) / (Ext)	10 % / 11 %
UV Rejection	99 %
IR Rejection	32 %
Solar Heat Gain Coefficient	0.77
Shading Coefficient	0.89
Total Solar Energy Rejection	23 %

AUTOMOTIVE FILMS

HAZE ★★★★★
SAFETY ★★
FADE OUT ★★★★★
SHIRINKAGE ★★★★
UV BLOCK ★★★★★
BLOCKS HEAT ★★★★★